

THERMOLITE™ SE

Technical Data Sheet

PRODUCT: Thermolite™ SE
EFFECTIVE: October 19, 2021

Description: Thermolite™ SE is an insulated glazing panel that consists of a fabricated Laminators Omega-Lite® ACM panel bonded to the exterior face of a Thermolite™ panel to create stepped edges. Intended for use in window, glazing, and curtain wall systems, panels are available in thicknesses ranging from 1-3/4 to 3-1/2 in.

Properties:

Thickness	2 in (nom), standard (1 in Thermolite™ + 1 in stepped edge Omega-Lite®)	
Weight	2.52 psf (+/-), standard	
Core	Expanded Polystyrene (EPS): 2.0 pcf density (Type IX)	Polyisocyanurate (ISO): 2.0 pcf density (Type I)
Stabilizers	Extruded Corrugated Polypropylene	
Sheets (ASTM B209)	3003-H14/24; 3105-H14/24 & H26/28; 5005-H34 Aluminum 0.012 to 0.032 in	
Stiffeners (ASTM B221)	6063-T4 Aluminum	
Texture Finish	Smooth (exterior), Smooth or Stucco-Embossed (interior)	
Color Finish (AAMA 2605)	PVDF/Kynar 500® or Anodized	
Thermal Expansion	13.1x10 ⁻⁶ in/in/°F	

R-Values: ¹

	EPS Core			ISO Core	
	Thickness (in)	R-Value ^{2,3} (hr °F ft ² / BTU)		Thickness (in)	R-Value ^{2,4} (hr °F ft ² / BTU)
	1-3/4	6.0		1-3/4	6.3
	2	7.0		2	7.6
	2-1/2	9.2		2-1/2	10.3
	3	11.4		3	13.0
	3-1/2	13.6		3-1/2	15.7

Go beyond the panel... and go to the next level!

Performance: ^{5,6}

Fire Performance (ASTM E84)	Class A (2 in w/ EPS) Flame Spread Index (FSI) = 0 Smoke Developed Index (SDI) = 100	Class A (1 in w/ ISO) Flame Spread Index (FSI) = 15 Smoke Developed Index (SDI) = 350
Fire Performance (Omega-Lite®) (ASTM E84)	Class A Flame Spread Index (FSI) = 15 Smoke Developed Index (SDI) = 90	

Available Load-Carrying Capacities (R_n / Ω): ^{7,8,9,10}

Panel Span (in) ¹¹	≤ 30	36	42	48	54	60
Wind Load (psf) ¹²	60	50	40	35	30	25

Notes:

- Linear interpolation between values is permitted.
- R-Values for 1 in (nom) standard Thermolite™ and 1 in (nom) standard Omega-Lite® portions of standard panel based on ASTM C518 Standard Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus performed by independent laboratory per ASHRAE 90.1-2010.
- Calculated values for all other panel thicknesses based on Carpenter Company published R-Value for 2.0 pcf density (Type IX) EPS foam at 75°F.
- Calculated values for all other panel thicknesses based on Elliot Company published aged R-Value for 2.0 pcf density (Type I) ISO foam.
- Surface-burning characteristics are applicable to exterior conditions only and are not applicable to interior conditions.
- Per International Building Code (IBC), panels shall be separated from the interior of a building with 1/2 in gypsum wallboard or other material tested in accordance with and meeting the acceptance criteria of NFPA 275.
- Based on testing performed in conjunction with ASTM E529 Standard Guide for Conducting Flexural Tests on Beams and Girders for Building Construction.
- Capacities are calculated for a 2 in (nom) standard panel with EPS core, actual sheet thickness, and 0.012 in sheet thickness on exterior face of Thermolite™ panel. Contact Laminators Technical Support for capacities of panels less than 2 in.
- Capacities are governed by the Aluminum Design Manual (ADM) using a Factor of Safety = 1.65 for yield strength.
- Project-specific Components and Cladding wind loads (Required Strength, R_a) shall not exceed Available Load-Carrying Capacities (Allowable Strength, R_n / Ω) for given spans. Wind loads are to be calculated per ASCE/SEI 7 Minimum Design Loads for Buildings and Other Structures.
- Panel Span applies to shortest dimension of finished panel.
- Strength conditions govern for given capacities; therefore, International Building Code (IBC) deflection limits have been met. Capacities are capped at values shown but are higher for spans less than indicated. Contact Laminators Technical Support if higher capacities are required.