

ALUMALITE® STANDARD

Technical Data Sheet

PRODUCT: Alumalite® Standard

EFFECTIVE: March 3, 2022

Description: Alumalite® Standard is a metal composite material (MCM) panel that consists of one or more thermoplastic cores bonded to a color finished sheet of aluminum on one face and a color or protected mill finished sheet of aluminum on the other. Panels are intended for use in digital print-ready sign panel applications.

Properties:

Thickness (standard)	6 mm (nom)	10 mm (nom)		
Weight	0.67 psf (+/-)	0.88 psf (+/-)		
Core	Extruded Corrugated	Extruded Corrugated Polypropylene		
	4.7 mm Core	(2) 4.7 mm Cores		
Sheets (ASTM B209)	3003-H26/28, 3105-H 0.012 in	3003-H26/28, 3105-H26/28 Aluminum 0.012 in		
Texture Finish	Smooth	Smooth		
Color Finish (AAMA 2605)	Polyester	Polyester		
Thermal Expansion	13.1x10 ⁻⁶ in/in/°F	13.1x10 ⁻⁶ in/in/°F		
Tolerances	(+/-) 1/4 in (Length & \	(+/-) 1/4 in (Length & Width) and (+/-) 1/32 in (Thickness)		
Squareness	Equal Within 1/8" (Dia	Equal Within 1/8" (Diagonals)		
Flatness	< 1/4 in / 4 ft (0.52%)	< 1/4 in / 4 ft (0.52%)		

Performance:

Fire Performance ¹ (ASTM E84)		
• Class	A	A
Flame Spread Index	0	5
Smoke Developed Index	60	200
Flexural Rigidity (EI) ² (ASTM E529)	2.40x10 ⁴ lb-in ² /ft	9.03x10 ⁴ lb-in ² /ft
	5 years against bond line delamination	
Warranty ³	10 years against color fade in excess of (8) NBS units and cracking, chipping, flaking, or peeling	



Notes:

- For 10 mm (nom) panel, testing was performed on 25 mm panel due to higher core (combustible) content. Class A results presented are conservatively extrapolated to 10 mm panel.

 Performed in conjunction with ASTM E529 Standard Guide for Conducting Flexural Tests on Beams and Girders for Building
- Construction.
- Contact Laminators Inc. for full warranty terms and conditions. 3.

UL File Number E60612